

TECHNICAL DATA SHEET


C690

APPLICATION: PAPER TAPE FOR PACKAGING – HOT MELT

Article	Backing Type	Backing Weight (g/m ²)	Adhesive Type	Total Thickness (μm)	Adhesion to Steel (N/cm) (AFERA 5001)	Tensile Strength (N/cm) (AFERA 5004)	Elongation at break (%) (AFERA 5004)
C690	Crepe Paper	72	Hot Melt	125	7,0	60	6,2
Tolerance				+/- 15%	+/- 10%	+/- 20%	+/- 25%

Adhesive tape: PAP22

Please follow your local disposal guidelines



FSC® declaration is referring to adhesive tape

Stocking time

We recommend to use the product within 6 months from the delivery.

Stocking conditions

Store the product in a clean dry place, at a temperature between 15°C and 25°C.
The product must be stored protected from dust, humidity and direct sun exposure.
It must be stored horizontally and kept in the original packaging.

Use

If the storage temperature has been different from what suggested, bring the tape back to that temperature before application.
Before applying the tape, remove any trace of dust or any other dirty from the application surface. Press the tape down thoroughly for a perfect and time lasting adherence.

Important:

The mentioned data stem from an average analysis carried out on our standard production and may undergo unexpected changes. Therefore they are not binding for our company.